SUPPORTING INFORMATION: Biomimetic SERS substrate: Peptide Recognition Elements for Highly Selective Chemical Detection in Chemically Complex Media

Saide Z. Nergiz¹, Naveen Gandra¹, Mikella E. Farrell², Limei Tian¹, Paul M. Pellegrino² and Srikanth Singamaneni¹*

¹Department of Mechanical Engineering and Materials Science, Washington University, St. Louis, MO 63130, United States

²U.S. Army Research Laboratory, Sensors and Electron Devices Directorate, Adelphi, Maryland 20783-1197, United States

FIGURES



Figure S1. Chemical structure and 3D molecular structure of TNT-binding peptide of sequence CGGGGGGGGGGGGGWHWQRPLMPVSI.

Electronic Supplementary Material (ESI) for Journal of Materials Chemistry A This journal is O The Royal Society of Chemistry 2013



Figure S2. (A) Raman spectra acquired from the paper substrate adsorbed with AuNR conjugated with peptide (CWHRYPSYLWGVI) that exhibits substantially weaker TNTbinding capability after exposure to 1 mM TNT. (B) Raman spectra of commercially available shampoo drop-casted on silicon. (C) Raman spectra of biomimetic plasmonic paper before and after exposure to 30 pg/cm³ of TNT vapour for 1 hour. (D) Raman spectra acquired of the biomimetic plasmonic paper before and after exposure to 10 pM TNT in 1 mg/ml shampoo solution.

Table S1. Corresponding Raman bands of TNT-binding peptide.

1	
Raman shift (cm ⁻)	Origin
670	C-S stretching
878	Tryptophan
1012	C-C aromatic ring stretching
1123	C-C, C-N stretching
1234-80	Amide III & CH ₂ wagging vibrations from glycine backbone
1266	Tryptophan
1302	Amide III
1341	Tryptophan
1360	Tryptophan
1552	Tryptophan
1580	C-C stretching
1619	Tryptophan