

Dye-sensitized solar cells containing plasma jet deposited hierarchical nanostructured TiO₂ thin photoanodes

by Vanira Trifiletti, Riccardo Ruffo, Christian Turrini, Dario Tassetti, Rosaria Brescia, Fabio di Fonzo, Claudia Riccardi, Alessandro Abbotto

Electronic Supplementary Information (ESI)

Table S1. Fitted parameters of the Nyquist plots using the equivalent circuit model.

TiO ₂ film	R _S [Ωcm ²]	R _{CE} [Ωcm ²]	Y _{CE} [Scm ⁻² s ⁿ]	n _{CE}	R _{rec} [Ωcm ²]	Y _{rec} [Scm ⁻² s ⁿ]	n _{rec}	W [Scm ⁻² s ^{-0.5}]	χ ²
1.2-μm PA-SJD	5.1	2.8	1.7x10 ⁻³	0.62	38	5.1x10 ⁻⁴	0.96	0.84	2.8x10 ⁻⁵
1.6-μm PA-SJD	2.8	1.9	5.2x10 ⁻³	0.59	33	8.2x10 ⁻⁴	0.96	1.8	6.6x10 ⁻⁵
2.2-μm PA-SJD	4.8	1.3	4.3x10 ⁻⁵	0.89	27	9.5x10 ⁻⁴	0.97	0.29	4.7x10 ⁻⁵
conventional monolayer	2.9	4.0	1.5x10 ⁻³	0.62	15	1.4x10 ⁻³	0.95	0.70	9.1x10 ⁻⁵