

Electronic Supporting Information (ESI) for

Synthesis of hierarchical fiberlike ordered mesoporous carbons with excellent electrochemical capacitance performance by a strongly acidic aqueous cooperative assembly route

Dan Liu,^{*a} Liang-Jun Xia,^a Deyu Qu,^a Jia-Heng Lei,^a Yu Li,^b Bao-Lian Su^{*bc}

^a Department of Chemistry, School of Science, Wuhan University of Technology, 122 Luoshi Road, Wuhan 430070, People's Republic of China. E-mail: daniellliu@whut.edu.cn; Fax: +86 27 8775 6662; Tel: +86 27 8775 6662

^b State Key Laboratory of Advanced Technology for Materials Synthesis and Processing, Wuhan University of Technology, 122 Luoshi Road, Wuhan 430070, People's Republic of China. E-mail: bao-lian.su@fundp.ac.be

^c Laboratory of Inorganic Materials Chemistry, University of Namur, 61 rue de Bruxelles, B-5000, Namur, Belgium




Fig. S1 (A) Wide-angle XRD pattern and (B) HR-TEM image of the carbon sample RF-4.8-50. Two broad diffraction peaks located at 23° and 44° (2θ) can be observed in the wide-angle XRD pattern, which can be assigned to the (002) and (100) of the graphite structure. The weak and broad peaks indicate very small domains of stacked crystalline graphite. No obvious graphitic fringe can be observed in the HR-TEM images. These results indicate the amorphous nature of the mesopore wall of the carbon sample.