

Supplementary information


Novel Core-Shell TiO₂ Microsphere Scattering Layer for Dye-Sensitized Solar Cells

Jiangwei Feng,^a Yang Hong,^a Jing Zhang,^{*a} Peiqing Wang,^a Ziyang Hu,^a Qing Wang,^a Liyuan Han^b and Yuejin Zhu^{*a}

^aDepartment of physics, Ningbo University, Ningbo 315211, Zhejiang, China. Fax: +86 574 87600744; Tel: +86 574 87600770; E-mail: zhangjing@nbu.edu.cn; zhuyuejin@nbu.edu.cn;

^bPhotovoltaic materials Unit, National Institute for Materials Science, Tsukuba, Japan

S-Fig. 1 SEM images of microstructure of Solid sphere TiO₂ (a) at low magnification and (b) at high magnification.



S-Table 1 Summary of the parameters of T, C-S-T and S-T.

Sample	S_{BET} (m^2/g)	pore size (nm)	pore volume (cm^3/g)
T	94	6.1	0.15
C-S-T	273	5.6	0.43
S-T	156	2.7	0.11