

Electronic Supplementary Information (ESI)

Multifunctional foams derived from poly(melamine formaldehyde) as recyclable oil absorbents

Yu Yang,^a Yonghong Deng,^{*,b} Zhen Tong^a and Chaoyang Wang^{*,a}




Fig. S1. EDS spectra of (a) PMF foam and (b) UFC foam. The mass amounts of carbon and nitrogen of PMF foam turn out to be 36% and 54%, respectively. The mass amount of nitrogen of UFC foam turns out to be 38%.




Fig. S2. The water wettability of (a) original and (b) pyrolysis-treated PMF foams.

The water contact angles turn out to be 0° , exhibiting superhydrophilicity.