

Supporting Information

High efficiency solution-processed small molecules solar cells featuring gold nanoparticles

Abd. Rashid bin Mohd Yusoff,^a Seung Joo Lee,^a Jin Jang,^a Guankui Long,^b Xiangjian Wan,^b
and Yongsheng Chen^b

^aAdvanced Display Research Center, Department of Information Display, Kyung Hee University, Dongdaemoon-gu, Seoul 130-701, Korea.

Email: abdr@khu.ac.kr

^bKey Laboratory of Functional Polymer Materials and the Centre of Nanoscale Science and Technology, Institute of Polymer Chemistry, College of Chemistry, Nankai University, Tianjin 300071, China.

Email: yschen99@nankai.edu.cn

Table S1. Photovoltaic parameters of plasmonic devices with different Au NPs concentrations.

Au NPs concentrations	J _{sc} (mA/cm ²)	V _{oc} (V)	FF (%)	PCE (%)
10wt%	13.86	0.92	65.91	7.58
20wt%	14.24	0.92	66.83	8.25
40wt%	14.42	0.92	67.31	8.92