

Electronic Supplementary Information for:

**Supramolecular hydrogel from inclusion complexation of
 α -cyclodextrin with densely grafted chains in micelles for
controlled drug and protein release**

Hui Zou^a, Wen Guo^a and Weizhong Yuan^{ab*}

^a*Institute of Nano and Bio-polymeric Materials, School of Materials Science and Engineering,
Tongji University, 4800 Cao'an Road, Shanghai 201804, People's Republic of China. Fax: +86
21 69584723; Tel: +86 21 69580234; E-mail: yuanwz@tongji.edu.cn*

^b*Key Laboratory of Advanced Civil Materials, Ministry of Education, 4800 Cao'an Road,
Shanghai 201804, People's Republic of China. Fax: +86 21 69584723; Tel: +86 21 69580234;
E-mail: yuanwz@tongji.edu.cn*




Fig. S1 DLS plots of Py-PCL-b-POEGMA micellar solutions with different concentrations

Table S1 DLS results of micelles with different concentrations

Concentration(mg/mL)	R_h (nm)	PDI
4	32.07	0.185
2	37.46	0.213
1	34.74	0.196
0.25	43.52	0.224
0.125	53.69	0.326




Fig. S2 The fluorescence intensity of the Py-PCL-*b*-POEGMA micellar solutions at different concentrations