Electronic Supplementary Material (ESI) for Journal of Materials Chemistry B. This journal is © The Royal Society of Chemistry 2014

Supporting information for:

Multi-responsive Hydrogels Derived from the Self-assembly of Tethered Allyl-functionalized Racemic Oligopeptides

Xun He, Jingwei Fan, Fuwu Zhang, Richen Li, Kevin A. Pollack, Jeffery E. Raymond, Jiong Zou* and Karen L. Wooley*

Departments of Chemistry, Chemical Engineering, and Materials Science and Engineering, Laboratory for Synthetic-Biologic Interactions, Texas A&M University, P.O. BOX 30012, 3255 TAMU, College Station, TX 77842 (USA). * Corresponding authors: Email: jiong.zou@chem.tamu.edu; wooley@chem.tamu.edu.

Tel: (979) 845-4077.

State ^b
Gel
Gel
Gel
Solution
Suspension

 Table S1
 Solubility studies of ODLAG₆-b-PEG₆₈-b-ODLAG₆ in different organic solvents.

^a The concentration of ODLAG₆-b-PEG₆₈-b-ODLAG₆ was 5.0 wt% in each solvent.

^b Observed after resting in room temperature for 72 h.



Fig. S1 MALDI-TOF mass spectrum of ODLAG₆-*b*-PEG₆₈-*b*-ODLAG₆.



Fig. S2 (a) Storage and loss moduli, and (b) $\tan(\delta)$ of ODLAG₆-*b*-PEG₆₈-*b*-ODLAG₆ hydrogel (5 wt%) as a function of frequency conducted by DMA at room temperature.



Fig. S3 (a) DSC trace of ODLAG₆-*b*-PEG₆₈-*b*-ODLAG₆ in the solid state. The samples were heated from -100 °C to 200 °C and cooled back to -100 °C with both heating and cooling rates of 10 °C/min. The third heating and cooling traces were shown here. (b) DSC trace of ODLAG₆-*b*-PEG₆₈-*b*-ODLAG₆ in the solid state, after rapid cooling above the T_m . The sample was removed from the DSC at 125 °C, immersed into liquid nitrogen and returned into the DSC during the second cycle. The third heating and cooling traces are shown here.



Fig. S4 TEM image of ODLAG₆-*b*-PEG₆₈-*b*-ODLAG₆ hydrogel.



Fig. S5 SEM image of ODLAG₆-*b*-PEG₆₈-*b*-ODLAG₆ hydrogel, after slight stretching to visualize internal features.