

Supporting Information

Biodegradable Glycopolymer-*b*-Poly(ϵ -caprolactone) Block Copolymer Micelles: Versatile Construction, Tailored Lactose Functionality, and Hepatoma-Targeted Drug Delivery

Wei Chen^{1, 2}, Fenghua Meng¹, Ru Cheng¹, Chao Deng¹, Jan Feijen^{1,2,*}, and Zhiyuan Zhong^{1,*}

¹ Biomedical Polymers Laboratory, and Jiangsu Key Laboratory of Advanced Functional Polymer Design and Application, Department of Polymer Science and Engineering, College of Chemistry, Chemical Engineering and Materials Science, Soochow University, Suzhou, 215123, P. R. China.

² Department of Polymer Chemistry and Biomaterials, Faculty of Science and Technology, MIRA Institute for Biomedical Technology and Technical Medicine, University of Twente, P.O. Box 217, 7500 AE Enschede, The Netherlands.

*Corresponding authors. Tel/fax: +86-512-65880098; E-mail: j.feijen@utwente.nl;

zyzhong@suda.edu.cn




Fig. S1 ^1H NMR spectra (400 MHz, CDCl_3) of PAC prepolymer (a) and PAC-*b*-PCL block copolymer (b).




Fig. S2 GPC traces of PAC block with a PDI of 1.23 and PAC-*b*-PCL block copolymer with a PDI of 1.78. The measurements were performed using chloroform as an eluent and polystyrene standards for the calibration of the columns.